



# HEGGEL® EL 3340

Abrasion-Resistant Soft Rubber Lining

*You Build, We Protect!*

**Description:**

**HEGGEL EL 3340** is a black soft rubber lining based on natural rubber (NR), designed for steel components exposed to extreme abrasion. It can be vulcanized in an autoclave for workshop applications or provided in a pre-vulcanized version with a 0.8 - 1 mm bonding layer for on-site installation. It provides abrasion resistance against moderately concentrated chemicals with high solid content and is especially suitable for drinking water applications. **HEGGEL EL 3340** exhibits excellent mechanical properties, particularly high abrasion resistance, along with outstanding flexibility across a wide temperature range. Additionally, it offers all the benefits of vulcanized rubber sheets, including resistance to mechanical stress after application.

**Characteristics:**

- Exceptional abrasion resistance for high-wear environments
- Good mechanical properties and flexibility across a wide temperature range
- Suitable for drinking water applications
- Thickness range between 3 and 6 mm (Depending on the requirements)

**Chemical Resistance:**

Information on the chemical resistance is available on request.

**Technical Data:**

Title	Standard	Value
Density	ASTM D297	0.97 ± 0.05 g/cm <sup>3</sup>
Abrasion Test	ISO 4649	≤ 65 mm <sup>3</sup>
Rebound Resilience	ISO 4662	70% (average)
Elongation	ASTM D412	≥ 700%
Stress at 100% Elongation	ASTM D 412	2 MPa
Hardness	ASTM D2240	38 ± 5 Shore A
Tensile Strength	ASTM D412	≥ 25 MPa

**Note:** These guidelines offer technical instructions, but real-case applications require common sense, professional judgment, and flexibility to achieve the best outcomes

**Note:** The values are derived from specimens produced under reproducible laboratory conditions. However, they may vary slightly in equipment linings due to the vulcanization conditions at the factory.

**Packaging:**

The adhesives are supplied in the following standard package sizes:

Product	Size	Package
HEGGEL Bond 2210 Primer	20 kg	Can
HEGGEL Bond 2235	20 kg	Can
Activator	0.7 kg	Can
Cleaning Solution	20 kg	Can

**Storage:**

The products must be stored in a dark and dry place at a temperature of max. 25°C in accordance with DIN 7716. The materials should not be exposed to freezing conditions, heat, flame, or spark. Check expiration dates and dispose of outdated and contaminated products. At the specified storage temperatures, a shelf life of the products is given of at least for the following periods:

Product	Temperature	Shelf Life
HEGGEL Bond 2210 Primer	20°C	24 Months
HEGGEL Bond 2235	20°C	12 Months
Activator	20°C	6 Months
Cleaning Solution	20°C	24 Months
HEGGEL EL 3340 Sheets	25°C	24 Months
HEGGEL EL 3340 Sheets	20°C	36 Months
HEGGEL EL 3340 Sheets	15°C	48 Months

Depending on storage conditions it may be possible to use rubber linings beyond the recommended shelf life however additional testing must be completed. Please contact HEGGEL for recommended test procedures. A sample of the rubber lining can also be sent back to HEGGEL for verification.

## 1. Surface Preparation

The substrate which is to be protected must meet the requirements contained in DIN 28051-97, DIN 28053-97, NACE RP0178-95. Bonding to both steel and concrete is possible. Bonding to other metallic substrates (such as titanium, copper, etc.) can be achieved provided that it is consulted with our technical department.

The metallic substrate must be blasted to achieve a minimum blast cleaning grade of SA 2½ with "medium" profile according to ISO 8501/1-95, ISO 8503/1/2-85 and SSPC SSPC-SP-5.

It is advisable to apply the primer to the blasted surface as soon as possible, and definitely before any traces of rust can reform.

If bonding to concrete is required, the substrate needs to be free of cement skin, cement slurry, loose and friable parts, defective spots and detaching material. The concrete needs to be blasted. The concrete surface has to have a residual moisture content of < 4%.

## 2. Environmental Conditions

The substrate must be dry and warmed if necessary, during application. Uncured material should be protected from moisture (condensation, fog, precipitation or other water source). Temperature of the substrate must be 3°C above the dew point temperature and should not be allowed to drop below that point throughout the lining process. (5°C dew point distance is highly recommended for ambient temperature lower than 10°C.)

## 3. Consumption

Component	Consumption per Coat	Number of Coats
<b>HEGGEL Bond 2210 Primer</b>	150 g/m <sup>2</sup>	1 coat
<b>HEGGEL Bond 2235</b>	200 g/m <sup>2</sup>	4 coats
<b>Activator</b>	3% W/W of the quantity of <b>HEGGEL Bond 2235</b>	-
<b>Cleaning Solution</b>	150 g/m <sup>2</sup>	1 coat

**Note:** The above value may change in the different work conditions.

## 4. Application

The adhesion cycle consists of **HEGGEL Bond 2210 Primer**, the two-component **HEGGEL Bond 2235** (requires activation), and a cleaning solution.

Apply one coat of **HEGGEL Bond 2210 Primer** to the blasted substrate and wash the **HEGGEL EL 3340** rubber sheet with the cleaning solution. Before use, activate **HEGGEL Bond 2235** by adding 3% (W/W) activator; the activated solution has a 60-minute pot life. Apply two coats on both the substrate and the rubber sheet layer to be bonded.

The rubber sheet should be applied once the adhesive solvents have dried to a touch-dry state. Wash the rubber sheets with the cleaning solution and bond them to the substrate following DIN 28055-1 specifications. Press the rubber sheet in accordance with DIN EN 14879-4 and DIN 28055/1-02. Finally, perform spark testing

as per DIN 28055/2-02 and NACE RP 0188-90 at 3 kV/mm.

## 5. Vulcanization

The rubber lining can be vulcanized in an autoclave or steam for workshop applications, but it is also available in a pre-vulcanized version for on-site application. Please contact HEGGEL.

## 6. Safety Measures

During the implementation of all work, ventilation must be ensured. Ventilation is mandatory for all work performed in pits and confined spaces. All the vapors generated during processing must be continuously exhausted at ground level or below. Only as much material as is necessary for the continuation of the work is to be stored at the work site. It must be observed and ensured that even the lowest quantities of each single component or the mixtures prepared shall not enter the sewage system. All local laws, regulations and international standards for accident prevention of the employer's liability insurance association need to be strictly adhered to.

The material safety data sheets of the individual components, the safety instructions on the packing (label) as well as the legal requirements for handling hazardous materials must be observed.

**HEGGEL EL 3340**; Revision No: 0.00 / Last Revision Date: 15.10.2024

All information contained herein is based on the current state of our knowledge and practical experience at the time of release. Therefore, please make sure that this is the latest edition of the Technical Data Sheet. All data are only intended as a guideline for informational purposes and do not constitute a legally-binding warranty of the suitability for a certain purpose of use, due to its dependence on site conditions and possible processing, use and applications. All information contained in this technical datasheet is subject to change without notice.

**HEGGEL GmbH**

Huttropstr. 60  
45138 Essen  
Germany

Tel: +49 201 17003 270

Fax: +49 201 17003 277

E-Mail: [info@heggel.de](mailto:info@heggel.de)

Web: [www.heggel.de](http://www.heggel.de)